



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>7</sup> :</b> <b>C08L 69/00, 51/04 // (C08L 69/00, 51:04)</b> <b>(C08L 51/04, 69:00)</b>	<b>A1</b>	<b>(11) International Publication Number: WO 00/56816</b> <b>(43) International Publication Date: 28 September 2000 (28.09.00)</b>
<b>(21) International Application Number:</b> PCT/US00/07616 <b>(22) International Filing Date:</b> 21 March 2000 (21.03.00) <b>(30) Priority Data:</b> 09/276,215 25 March 1999 (25.03.99) US <b>(71) Applicant:</b> BAYER CORPORATION [US/US]; 100 Bayer Road, Pittsburgh, PA 15205 (US). <b>(72) Inventors:</b> SPANGLER, Lora, L.; 39 Segur Lane, Belcher-town, MA 01007 (US). JANARTHANAN, Venkatarayaloo; 15 Green Park Society, Tandalja Road, Vadodara, Gujarat 390 020 (IN). <b>(74) Agents:</b> PREIS, Aron et al.; Bayer Corporation, Patent Dept., 100 Bayer Road, Pittsburgh, PA 15205 (US).	<b>(81) Designated States:</b> AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
<b>(54) Title:</b> COMPOSITIONS CONTAINING POLYCARBONATE AND GRAFTED RUBBER HAVING IMPROVED LOW-TEMPERATURE TOUGHNESS  <b>(57) Abstract</b>  A thermoplastic molding composition suitable for preparing molded articles having improved properties, most notably high ductility and impact strength at low temperature, is disclosed. The composition contains a resinous blend of aromatic polycarbonate and a mixture of at least two grafted rubbers. The mixture of grafted rubbers contains a "small-mode" component having a weight average particle size of less than 0.3 microns and a "large-mode" component having a weight average particle size of 0.3 microns or larger.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

COMPOSITIONS CONTAINING POLYCARBONATE AND GRAFTED  
RUBBER HAVING IMPROVED LOW-TEMPERATURE TOUGHNESS

FIELD OF THE INVENTION

The present invention relates to a thermoplastic molding composition and more particularly to a composition containing polycarbonate and grafted rubber.

SUMMARY OF THE INVENTION

5           A thermoplastic molding composition suitable for preparing molded articles having improved properties, most notably high ductility and impact strength at low temperature, is disclosed. The composition contains a resinous blend of aromatic polycarbonate and a mixture of at least two grafted rubbers. The mixture of grafted rubbers contains a "small-mode"  
10       component having a weight average particle size of less than 0.3 microns and a "large-mode" component having a weight average particle size of 0.3 microns or larger.

TECHNICAL BACKGROUND OF THE INVENTION

15           Thermoplastic molding compositions containing grafted rubber, such as ABS, and polycarbonate resin are known. Commercial products based on such compositions, notably Bayblend compositions that are available from Bayer Corporation, have long enjoyed wide market acceptance. U.S. Patents 3,954,905 and 4,560,725 are noted to have disclosed relevant compositions. Also known are compositions which  
20       include ABS components, the rubber particles of which conform to bimodal size distributions. The art is noted to include U.S. Patent 3,509,237 which disclosed a composition containing first and second graft copolymers having a rubber substrate and a superstrate of an interpolymer of a monovinylidene aromatic hydrocarbon and an unsaturated nitrile. The first  
25       and second graft copolymers have a number average particle size, of 0.8 to 2.0 microns and 0.01 to 0.25 microns respectively. The first graft is said

- 2 -

to be a product of suspension polymerization and the second is produced by emulsion. U.S. Patent 4,677,162 is noted for its disclosed composition, which contains polycarbonate, a graft copolymer and an impact modifier. While the graft copolymer entails particles averaging more than 0.75  
5    microns, the impact modifier entailed in the working examples embraces a second graft copolymer having presently relevant chemical makeup and particle size.

#### DETAILED DESCRIPTION OF THE INVENTION



The inventive composition contains a resinous blend of about 60 to  
10    80 percent polycarbonate resin and 20 to 40 percent of a mixture of at least two grafted rubbers. In a preferred embodiment, the blend contains 65 to 75 percent polycarbonate and 25 to 35 percent of the mixture; in all instances, the percents are in relation to the weight of the blend. The mixture of grafted rubbers contains a "small-mode" component (ABS-s)  
15    having a weight average particle size smaller than 0.3 microns, preferably about 0.15 to 0.28 microns, and a "large-mode" component (ABS-l), wherein weight average particle size is at least 0.3 micron, preferably about 0.35 to 0.65 micron. The weight ratio ABS-s/ABS-l in the mixture ranges from 3/27 to 7.5/22.5, preferably 3/27 to 5/25. In the preferred  
20    embodiments, ABS-s is a product of the well-known emulsion polymerization process and ABS-l is a product of the known mass, more preferably continuous mass, polymerization process.

The aromatic polycarbonate resins useful in the context of the present invention include homopolycarbonates and copolycarbonates and  
25    mixtures thereof. The suitable polycarbonates have a weight average molecular weight of 10,000 to 200,000, preferably 20,000 to 80,000 and their melt flow rate, per ASTM D-1238 at 300°C, is about 1 to about 65 g/10 min., preferably about 2 to 24 g/10 min. These resins may be prepared, for example, by the known diphasic interface process from a  
30    carbonic acid derivative such as phosgene and dihydroxy compounds by

- 3 -

polycondensation (see German Offenlegungsschriften 2,063,050; 2,063,052; 1,570,703; 2,211,956; 2,211,957 and 2,248,817; French Patent 1,561,518; and the monograph H. Schnell, "Chemistry and Physics of Polycarbonates", Interscience Publishers, New York, New York, 1964, all incorporated herein by reference).

In the present context, dihydroxy compounds suitable for the preparation of the polycarbonates of the inventor conform to the structural formulae (1) or (2).




25 wherein

A denotes an alkylene group with 1 to 8 carbon atoms, an alkylidene group with 2 to 8 carbon atoms, a cycloalkylene group with 5 to 15 carbon atoms, a cycloalkylidene group with 5 to 15 carbon atoms, a carbonyl group, an oxygen atom, a sulfur atom, -SO-, or -SO<sub>2</sub>- or a radical conforming to

30

- 4 -



5

e and g both denote the number 0 to 1; Z denotes F, Cl, Br or C<sub>1-4</sub>-alkyl and if several

Z radicals are substituents in one aryl radical, they may be identical or different from one another;

10 d denotes an integer of from 0 to 4; and

f denotes an integer of from 0 to 3.

Among the dihydroxy compounds useful in the practice of the invention are hydroquinone, resorcinol, bis-(hydroxyphenyl)-alkanes, bis-(hydroxyphenyl)-ethers, bis-(hydroxyphenyl)-ketones, bis-(hydroxyphenyl)-sulfoxides, bis-(hydroxyphenyl)-sulfides, bis-(hydroxyphenyl)-sulfones, and  $\alpha,\alpha$ -bis-(hydroxyphenyl)-diisopropylbenzenes, as well as their nuclear-alkylated compounds. These and further suitable aromatic dihydroxy compounds are described, for example, in U.S. Patents

15 5,126,428; 5,104,723; 5,041,521; 5,034,457; 3,028,356; 2,999,835; 3,148,172; 2,991,273; 3,271,367; and 2,999,846, all incorporated herein by reference.

20

Further examples of suitable bisphenols are 2,2-bis-(4-hydroxyphenyl)-propane (bisphenol A), 2,4-bis-(4-hydroxyphenyl)-2-methylbutane, 1,1-bis-(4-hydroxyphenyl)-cyclohexane,  $\alpha,\alpha'$ -bis-(4-hydroxyphenyl)-p-diisopropylbenzene, 2,2-bis-(3-methyl-4-hydroxyphenyl)-propane, 2,2-bis-(3-chloro-4-hydroxyphenyl)-propane, bis-(3,5-dimethyl-4-hydroxyphenyl)-methane, 2,2-bis-(3,5-dimethyl-4-hydroxyphenyl)-propane, bis-(3,5-dimethyl-4-hydroxyphenyl)-sulfide, bis-(3,5-dimethyl-4-hydroxyphenyl)-sulfoxide, bis-(3,5-dimethyl-4-hydroxyphenyl)-sulfone, dihydroxybenzophenone, 2,4-bis-(3,5-dimethyl-4-hydroxyphenyl)-cyclohexane,  $\alpha,\alpha'$ -

25

30

- 5 -

bis-(3,5-dimethyl-4-hydroxyphenyl)-p-diisopropyl-benzene and 4,4'-sulfonyl diphenol.

Examples of particularly preferred aromatic bisphenols are 2,2-bis-(4-hydroxyphenyl)-propane, 2,2-bis-(3,5-dimethyl-4-hydroxyphenyl)-propane and 1,1-bis-(4-hydroxyphenyl)-cyclohexane.

The most preferred bisphenol is 2,2-bis-(4-hydroxyphenyl)-propane (bisphenol A).

The polycarbonates of the invention may entail in their structure units derived from one or more of the suitable bisphenols.

Among the resins suitable in the practice of the invention is included phenolphthalein-based polycarbonate, copolycarbonates and terpolycarbonates such as are described in U.S. Patents 3,036,036 and 4,210,741, both incorporated by reference herein.

The polycarbonates of the invention may also be branched by condensing therein small quantities, e.g., 0.05 to 2.0 mol % (relative to the bisphenols) of polyhydroxyl compounds.

Polycarbonates of this type have been described, for example, in German Offenlegungsschriften 1,570,533; 2,116,974 and 2,113,374; British Patents 885,442 and 1,079,821 and U.S. Patent 3,544,514. The following are some examples of polyhydroxyl compounds which may be used for this purpose: phloroglucinol; 4,6-dimethyl-2,4,6-tri-(4-hydroxyphenyl)-heptane; 1,3,5-tri-(4-hydroxyphenyl)-benzene; 1,1,1-tri-(4-hydroxyphenyl)-ethane; tri-(4-hydroxyphenyl)-phenylmethane; 2,2-bis-[4,4-(4,4'-dihydroxydiphenyl)]-cyclohexyl-propane; 2,4-bis-(4-hydroxy-1-isopropylidene)-phenol; 2,6-bis-(2'-dihydroxy-5'-methylbenzyl)-4-methylphenol; 2,4-dihydroxybenzoic acid; 2-(4-hydroxyphenyl)-2-(2,4-dihydroxyphenyl)-propane and 1,4-bis-(4,4'-dihydroxytriphenylmethyl)-benzene. Some of the other polyfunctional compounds are 2,4-dihydroxybenzoic acid, trimesic acid, cyanuric chloride and 3,3-bis-(4-hydroxyphenyl)-2-oxo-2,3-dihydroindole.

- 6 -

In addition to the polycondensation process mentioned above, other processes for the preparation of the polycarbonates of the invention are polycondensation in a homogeneous phase and transesterification. The suitable processes are disclosed in the incorporated herein by reference, 5 U.S. Patents 3,028,365; 2,999,846; 3,153,008; and 2,991,273.

The preferred process for the preparation of polycarbonates is the interfacial polycondensation process.

Other methods of synthesis in forming the polycarbonates of the invention such as disclosed in U.S. Patent 3,912,688, incorporated herein 10 by reference, may be used.

Suitable polycarbonate resins are available in commerce, for instance, Makrolon 2400, Makrolon 2600, Makrolon 2800 and Makrolon 3100, all of which are bisphenol based homopolycarbonate resins differing in terms of their respective molecular weights and characterized in that 15 their melt flow indices (MFR) per ASTM D-1238 are about 16.5 to 24, 13 to 16, 7.5 to 13.0 and 3.5 to 6.5 g/10 min., respectively. These are products of Bayer Corporation of Pittsburgh, Pennsylvania.

Polycarbonate resins suitable in the practice of the invention are known and their structures and methods of preparation have been 20 disclosed, for example in U.S. Patents 3,030,331; 3,169,121; 3,395,119; 3,729,447; 4,255,556; 4,260,731; 4,369,303 and 4,714,746 all of which are incorporated by reference herein.

The mixture included in the inventive composition contains a "small-mode" component (ABS-s) having a weight average particle size smaller 25 than 0.3 microns, preferably 0.15 to 0.28 micron, and a "large-mode" component (ABS-l) having a weight average particle size of at least 0.3 micron, preferably 0.35 to 0.65 micron. The weight ratio ABS-s/ABS-l in the mixture ranges from 3/27 to 7.5/22.5, preferably 3/27 to 5/25.

The grafted phase in both grafted rubber components of the instant 30 mixture contains a monovinylidene aromatic hydrocarbon and an



- 7 -

unsaturated nitrile. Such monomers comprise at least 50.0 percent by weight, preferably at least 75 percent by weight of the grafted phase. Most desirably, such monomers comprise at least 90 percent of the grafted phase. Minor amounts, preferably less than 10 percent of other

5 comonomers may be included. Examples of the monovinylidene aromatic hydrocarbons which may be used in the preparation of the grafted phase include styrene, alpha-alkyl monovinylidene monoaromatic compounds, e.g., alpha-methylstyrene, alpha-ethylstyrene, alpha-methyl-vinyltoluene, alpha-methyl dialkylstyrenes, etc., ring-substituted alkyl styrenes, e.g.,

10 vinyl toluene, o-ethylstyrene, p-ethylstyrene, 2,4-dimethylstyrene, etc., ring-substituted halostyrenes, e.g., o-chlorostyrene, p-chlorostyrene, o-bromostyrene, 2,4-dichlorostyrene, etc., ring-alkyl, ring-halosubstituted styrenes, e.g., 2-chloro-4-methylstyrene, 2,6-dichloro-4-methylstyrene, etc., vinyl naphthalene; vinyl anthracene, etc. The alkyl substituents

15 generally have 1 to 4 carbon atoms and may include isopropyl and isobutyl groups. If so desired, mixtures of such monovinylidene aromatic monomers may be employed.

Examples of the unsaturated nitriles, which may, singly or in combination one with the others, be used in the preparation of the grafted

20 phase include acrylonitrile, methacrylonitrile, and ethacrylonitrile.

Examples of additional monomers which may be copolymerized in small amounts in the grafted phase include conjugated 1,3 dienes, e.g., butadiene, isoprene, etc.; alpha- or beta-unsaturated mono-basic acids and derivatives thereof, e.g., acrylic acid, methyl acrylate, ethyl acrylate,

25 butyl acrylate, 2-ethylhexyl acrylate, methacrylic acid and the corresponding esters thereof, acrylamide, methacrylamide; vinyl halides such as vinyl chloride, vinyl bromide, etc.; vinylidene chloride, vinylidene bromide, etc.; vinyl esters such as vinyl acetate, vinyl propionate, etc.; dialkyl maleates or fumarates such as dimethyl maleate, diethyl maleate,

30 dibutyl maleate, the corresponding fumarates, etc.

The polymerizable monomer mixture forming the grafted phase contains at least 20 percent by weight of the monovinylidene aromatic monomer and preferably at least 50 percent by weight thereof. They also contain at least 5 percent by weight of the unsaturated nitrile and preferably at least 10 percent by weight thereof. From the standpoint of highly advantageous commercial practice, the monomer formulations contain 20 to 95 percent, and preferably 60 to 85 percent, by weight of the vinylidene aromatic hydrocarbon and 80 to 5 percent, and preferably 40 to 15 percent, by weight of the unsaturated nitrile.

10 The rubber substrate in both grafted rubber components onto which the grafted phase is grafted during the polymerization process and in the presence thereof is a diene rubber. These are prepared of one or more conjugated 1,3-dienes, such as, butadiene, isoprene, piperylene, chloroprene, etc. Such rubbers include homopolymers and interpolymers of  
15 conjugated 1,3-dienes with up to an equal amount by weight of one or more copolymerizable monoethylenically unsaturated monomers, such as monovinylidene aromatic hydrocarbons (e.g., styrene; an aralkyl-styrene, such as the o-, m-, and p-methylstyrenes, 2,4-dimethylstyrene, the ar-ethyl-styrenes, p-tert-butylstyrene, etc.; an alpha-alkylstyrene, such as  
20 alpha-methylstyrene, alpha-ethylstyrene, alpha-methyl-p-ethylstyrene, etc.; vinyl naphthalene, etc.); arhalo monovinylidene aromatic hydrocarbons (e.g., the o-, m-, and p-chlorostyrenes, 2,4-dibromostyrene, 2-methyl-4-chlorostyrene, etc.); acrylonitrile; methacrylonitrile; alkyl acrylates (e.g., methyl acrylate, butyl acrylate, 2-ethylhexyl acrylate, etc.), the  
25 corresponding alkyl methacrylates; acrylamides (e.g., acrylamide, methacrylamide, N-butyl acrylamide, etc.); unsaturated ketones (e.g., vinyl methyl ketone, methyl isopropenyl ketone, etc.); alpha-olefins (e.g., ethylene, propylene, etc.); pyridines; vinyl esters (e.g., vinyl acetate, vinyl stearate, etc.); vinyl and vinylidene halides (e.g., the vinyl and vinylidene  
30 chlorides and bromides, etc.); and the like.

- 9 -

The rubber substrate may be crosslinked by the addition into the polymerizable mixture up to about 2 percent, relative to the weight of the rubber forming monomers, of a conventional crosslinking agent, such as divinylbenzene, diallyl sebacate, diallyl fumarate, diallyl adipate, allyl acrylate, allyl methacrylate, diacrylates and dimethacrylates of polyhydric alcohols, such as ethylene glycol dimethacrylate.

A preferred group of rubbers are those consisting essentially of 75 to 100 percent by weight of butadiene and/or isoprene and up to 25 percent by weight of a monomer selected from the group consisting of monovinylidene aromatic hydrocarbons (e.g., styrene) and unsaturated nitriles (e.g., acrylonitrile), or mixtures thereof. Particularly advantageous substrates are butadiene homopolymer or an interpolymers of 90 to 95 percent by weight butadiene and 5 to 10 percent by weight of acrylonitrile or styrene.

Preferably, the ABS-s component of the invention is made by the known emulsion polymerization process. Its rubber substrate amounts to about 50 to 60% relative to its weight and the grafted phase is characterized in that the weight ratio of the polymerized monovinylidene aromatic hydrocarbons to the polymerized unsaturated nitriles is 70-80/30-20, preferably 75-78/25-22.

In the emulsion polymerization process, the monomers and rubber substrate are emulsified in water by use of suitable emulsifying agents such as fatty acid soaps, alkali metal or ammonium soaps of high molecular weight alkyl or alkaryl sulfates and sulfonates, mineral acid salts of long chain aliphatic amines, etc. Emulsifying agents which have proven particularly advantageous are sodium oleate, sodium palmitate, sodium stearate and other sodium soaps. Generally, the emulsifying agent is provided in amounts of about 1 to 15 parts by weight per 100 parts by weight of the monomers, and water is provided in an amount of about 1 to

- 10 -

4 parts per part of monomers, and even in larger ratios where greater dilution is desirable.

If so desired, aqueous latex formed in the emulsion polymerization of the rubber substrate may provide the aqueous medium into which the monomers are incorporated with or without additional emulsifying agents, etc. However, the rubber may be dissolved in the monomers and the mixture emulsified, or a latex thereof may be separately prepared.

Various water-soluble free radical polymerization initiators are conventionally used for emulsion polymerization of the rubber monomer including conventional peroxy and perazo catalysts and the resultant latex may be used as the aqueous medium with which the interpolymer monomers are admixed. In this manner, the catalyst for the rubber polymerization may function in whole or in part as the catalyst for the graft polymerization. However, additional catalyst may be added at the time of graft polymerization. Exemplary of suitable peroxy catalysts are the alkali metal peroxides, persulfates, perborates, peracetates, and percarbonates, and hydrogen peroxide. If so desired, the catalysts may be activated to form redox systems. In addition, it may be advantageous to include an oil-soluble catalyst such as those hereinbefore identified for mass-emulsion polymerization processes. However, other free-radical generating catalysts may be employed such as actinic radiation.

Chain transfer agents and other polymerization modifiers may desirably be included and it is generally advantageous to incorporate a higher alkyl mercaptan, such as tert-dodecyl mercaptan, which acts both as a promoter and a regulator. In addition, antioxidants and stabilizers such as the alkylated phenols may be added.

The emulsion mixture is then polymerized in an inert atmosphere at temperatures in the range of 20 to 100° centigrade with agitation. Pressures of 1 to 100 pounds per square inch may be employed and the monomers and/or additional catalyst may be added incrementally or

- 11 -

continuously over a portion of the reaction cycle. Polymerization is continued until substantially all, i.e., more than 90 percent, of the monomers have reacted. The remaining monomers and other volatile components are then distilled from the latex, which is then dewatered, and  
5 dried.

The ABS-I component of the inventive composition is preferably made by the known mass, more preferably continuous mass polymerization process. The rubber in this graft copolymer is preferably butadiene or butadiene/styrene copolymer (90/10 by weight) and the  
10 rubber content is about 14 to 20% relative to the weight of the graft copolymer. The grafted phase is characterized in that the weight ratio of the polymerized monovinylidene aromatic hydrocarbons to the polymerized unsaturated nitriles is 73-80/27-20, preferably 75-78/25-22.

In the continuous mass polymerization process, the rubber  
15 substrate is initially dissolved in the monomers and the solution, initiator and any other optional components such as a solvent are continuously charged to a stirred or unstirred reactor which provides a continuous polymerization zone containing the polymerizing mixture with a substantially uniform composition throughout. A plurality of reactors may  
20 be employed in series with each operating in a continuous mode in which the polymerization is advanced to the required conversion. After polymerization has progressed to the desired conversion level, the residual monomer is stripped from the polymer. The devolatilizing operation, which is the same whether one or a series of polymerization  
25 reactors is employed, is conventionally done in a separate device such as a wiped film or falling strand devolatilizer.

Typical prior art processes for the continuous production of grafted rubbers by mass polymerization are described in U.S. Patents 3,243,481, 3,337,750, 3,511,895 and 4,417,030, the content of the latter being  
30 incorporated herein by reference.

- 12 -

The polymerization may be initiated by any free radical generating initiator that promotes grafting and is activated at the contemplated reaction temperatures. Suitable initiators comprise the conventional monomer-soluble peroxy and perazo compounds. Exemplary initiators are

5 t-butyl-peroxy-neodecanoate, t-butyl-peroxy-2-ethylhexanoate, 1-t-butyl-azo-1-cyanocyclohexane, di-tert-butyl peroxide, benzoyl peroxide lauroyl peroxide, oleyl peroxide, toluyl peroxide, di-tert-butyl diperphthalate, tert-butyl peracetate, tert-butyl perbenzoate, dicumyl peroxide, tert-butyl peroxide isopropyl carbonate, 2,5-dimethyl-2,5-di-(tert-butylperoxy)

10 hexane, 2,5-dimethyl-2,5-di-(tert-butylperoxy)-hexyne-3, tert-butyl hydroperoxide, bumene hydroperoxide, p-methane hydroperoxide, cyclopentane, hydroperoxide, diisopropylbenzene hydroperoxide, p-tert-butylcumene hydroperoxide, penant hydroperoxide, 2,5-dimethylhexane-2,5-dihydroperoxide, as well as percarbonate compounds such as t-butyl-

15 2-ethylhexyl-monoperoxycarbonate, etc. and mixtures thereof.

The initiator is generally included within the range of 0.001 to 1.0 percent by weight, and preferably on the order of 0.005 to 0.5 percent by weight of the polymerizable material, depending upon the monomers and the desired polymerization cycle.

20 It is often desirable to incorporate molecular weight regulators such as mercaptans, halides and terpenes in relatively small percentages by weight, on the order of 0.001 to 1.0% by weight of the polymerizable material. In addition, it may be desirable to include relatively small amounts of antioxidants or stabilizers such as the conventional alkylated

25 phenols. Alternatively, these may be added during or after polymerization. The formulation may also contain other additives such as plasticizers, lubricants, colorants and non-reactive preformed polymeric materials which are suitable or dispersible therein.

A solvent or diluent can be used to dilute the reaction mixture to a

30 point at which the power requirements for agitation in stirred reactor(s) are

- 13 -

not excessive. Some or all of such diluents can be introduced with the rubber in monomer solution either as an added component or by use of a rubber which is already dissolved in a suitable solvent. Diluent can also be added separately to one or more of the reactors.

5           The diluents can be liquid aromatic hydrocarbons containing 6 to 10 carbon atoms, e.g., benzene, toluene, xylene, ethyl benzene, para cymene, cumene or mixtures thereof. Other organic solvents such as saturated aliphatic hydrocarbons, e.g., hexane, cyclohexane, cyclopentane and others having 5 to 7 carbon atoms, ketones, e.g., methyl ethyl ketone,  
10 methyl cyclopentane, methyl isobutyl ketone, cyclohexane or methyl propyl ketone can also be used. Methylethyl ketone is preferred.

A preferred continuous mass process for separately preparing ungrafted matrix copolymer is disclosed in U.S. Patent 3,813,369 which is incorporated herein by reference. In summary, the monomers are  
15 continuously charged to a well-mixed polymerization reaction zone comprising liquid and vapor phases. The liquid phase contains the monomer composition as a solvent in which copolymer being formed from the monomer composition is dissolved. The vapor phase above the liquid phase comprises the monomer composition. Liquid and vapor are  
20 continuously removed from the reaction zone and replenished by charging at a rate about equal to the rate at which the monomers are polymerized and removed. The removed vapor phase may be condensed by reflux condensation and returned to the reaction zone as part of the monomer composition being charged to the zone. The mixture of withdrawn polymer  
25 and monomer is passed through one or more devolatilizers of the type referred to above to separate out the polymer. The hot melt may then be pelletized in conventional apparatus while the separated monomer is condensed and returned to the reaction zone. Chain transfer agents and liquid solvents, initiators, and other additives of the type described above  
30 with respect to the continuous mass graft polymerization process may be

- 14 -

charged continuously with the monomer composition or separately to the reaction zone.

The average particle size of a rubber graft copolymer - i.e., the rubber substrate and its graft copolymer superstrate, is based upon the average of the particles of the several sizes in each rubber graft copolymer component. Particle size is measured using a photosedimentometer by the published procedure of Graves, M. J. et. al. "Size Analysis of Subsieve Powders Using a Centrifugal Photosedimentometer", British Chemical Engineering 9:742- 744 (1964). Alternatively an electron microscope may be used.

The inventive composition may be prepared and processed conventionally by means and the following procedures that are well known to the art-skilled.

#### EXAMPLES

Compositions demonstrating the invention have been made and their properties were determined. The table below summarizes the results of the evaluation. In preparing the composition, the following components were used:

Polycarbonate: a homopolycarbonate based on bisphenol A, having a melt flow rate of about 11 gm/10 min. as determined in accordance with ASTM D-1238.

ABS-I (a): a graft copolymer containing 16% butadiene/styrene (90/10 wt.%) rubber and having the ratio of S/AN of 77/23, having a particle size, weight average, of 0.64 microns.

ABS-I (b): a graft copolymer containing 16% butadiene/styrene (90/10 wt.%) rubber and having the ratio of S/AN of 77/23, having a particle size, weight average, of 0.35 microns.

ABS-s: a graft copolymer containing 53% butadiene rubber, and having SAN ratio of 73/27 and a weight average particle size of 0.28 microns.



- 15 -

SAN: a copolymeric phase having a ratio of styrene/acrylonitrile of 72.5/27.5.

- The Vicat temperature was determined in accordance with ASTM 1525; Izod impact strength, in accordance with ASTM D 256; Multiaxial impact strength, in accordance with ASTM D3763 (test velocity 6.7 m/s; striker mass selected to minimize velocity loss during impact.) Ductility: the definition of ductile failure for the examples presented in the table below, is based on General Motors Engineering standard GMP.ABS+PC.002. Using the multiaxial impact test, a test specimen is deemed to have exhibited ductile failure if the puncture of the test specimen is accompanied by cracks radiating no more than 10 mm beyond the center of the impact point. The reported ductile failures denote the percents of the specimens failed in this fashion, out of the fifteen specimens tested.
- The compositions also contained a mold release agent and an antioxidant in conventional amounts, having no criticality in the context of the invention. The compositions of the invention (represented by Examples 1, 2, 3 and 4) are set in comparison to a corresponding composition, Example 5, which although containing a corresponding amount of rubber and exhibits largely identical or better Vicat properties and Izod impact strength, is characteristically more brittle at low temperature than are the inventive compositions.

	1	2	3	4	5 (Com.)
Polycarbonate	70	70	70	70	70
ABS-I(a)	30	27			
ABS-I(b)			30	27	
ABS-s		3		3	13
SAN					17
<b>Total Rubber</b>	4.8	5.91	4.8	5.91	6.89
Properties					
Vicat temperature (°C) 1Kg@120°C/hr	144	144.9	144.2	144.3	145
Impact Strength, Izod (ft-lb/in)					
1/8" At 23°C	11.7	10.9	10.9	11	11.5
1/8" At -30°C	5.3	7.1	5.7	7.8	9
multiaxial Impact strength, at -30°C (J)					
(Emax)	50	56	52	51	46
(Efail)	55	60	56	56	48
Brittle/Ductile	9/6	1/14	10/5	2/13	10/0
Ductile failures, percent	40	93	33	87	0

- 17 -

Although the invention has been described in detail in the foregoing for the purpose of illustration, it is to be understood that such detail is solely for that purpose and that variations can be made therein by those skilled in the art without departing from the spirit and scope of the invention except as it may be limited by the claims.

WHAT IS CLAIMED IS:

1. A thermoplastic molding composition comprising a blend of
  - (i) 60 to 80 percent polycarbonate resin and
  - (ii) 20 to 40 percent of a mixture of at least two grafted rubbers,
- 5 said percents being in relation to the weight of the blend,  
wherein mixture contains a small-mode component containing a grafted  
rubber having a particle size, weight average, smaller than 0.3 micron and  
a large-mode component containing a grafted rubber having a particle  
size, weight average of at least 0.3 microns, said mixture further
- 10 characterized in that said small-mode component and large mode  
component are present in the blend at a weight ratio of 3/27 to 7.5/22.5  
therebetween.
2. The thermoplastic molding composition of Claim 1 wherein  
said blend contains 65 to 75 percent polycarbonate and 25 to 35 percent
- 15 of said mixture.
3. The thermoplastic molding composition of Claim 1 wherein  
said range is 3/27 to 5/25.
4. The thermoplastic molding composition of Claim 1 wherein  
said small mode component is a product of emulsion polymerization.
- 20 5. The thermoplastic molding composition of Claim 1 wherein  
said large mode component is a product of mass polymerization.
6. The thermoplastic molding composition of Claim 1 wherein  
said large mode component is a product of continuous mass  
polymerization.
- 25 7. The thermoplastic molding composition of Claim 1 wherein  
small-mode component has a particle size, weight average, of 0.15 to 0.28  
microns.
8. The thermoplastic molding composition of Claim 1 wherein  
said large-mode component has a particle size, weight average, of 0.35 to
- 30 0.65 microns.

- 19 -

9. The thermoplastic molding composition of Claim 1 wherein said small mode component contains rubber at an amount of 50 to 60% relative to its weight.

10. The thermoplastic molding composition of Claim 9 wherein  
5 said small mode component contains a grafted phase, polymerized monovinylidene aromatic hydrocarbons and polymerized unsaturated nitriles in a weight ratio of 70-80/30-20 therebetween.

11. The thermoplastic molding composition of Claim 9 wherein  
10 said small mode component contains a grafted phase, polymerized monovinylidene aromatic hydrocarbons and polymerized unsaturated nitriles in a weight ratio of 75-78/25-22 therebetween.

12. The thermoplastic molding composition of Claim 1 wherein said large mode component contains rubber at an amount of 14 to 20% relative to its weight.

13. The thermoplastic molding composition of Claim 12 wherein  
15 said large mode component contains a grafted phase, polymerized monovinylidene aromatic hydrocarbons and polymerized unsaturated nitriles in a weight ratio of 70-80/30-20 therebetween.

14. The thermoplastic molding composition of Claim 12 wherein  
20 said large mode component contains a grafted phase, polymerized monovinylidene aromatic hydrocarbons and polymerized unsaturated nitriles in a weight ratio of 75-78/25-22 therebetween.

International Application No  
PCT/US 00/07616

According to International Patent Classification (IPC) or to both national classification and IPC

Minimum documentation searched (classification system followed by classification symbols)

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

### C. DOCUMENTS CONSIDERED TO BE RELEVANT

<input checked="" type="checkbox"/>	Further documents are listed in the continuation of box C.	<input checked="" type="checkbox"/>	Patent family members are listed in annex.
-------------------------------------	--	-------------------------------------	--

\* Special categories of cited documents :

\*& document member of the same patent family

Date of mailing of the international search report

11/08/2000

Authorized officer

Russell, G

## INTERNATIONAL SEARCH REPORT

Int. lional Application No  
PCT/US 00/07616

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 677 162 A (MOBAY CORPORATION) 30 June 1987 (1987-06-30) cited in the application column 6, line 25 - line 29 examples claims 1-5,7,9 -----	1-14
X	US 4 868 235 A (BASF AG) 19 September 1989 (1989-09-19) column 1, line 66 -column 2, line 4; examples claims 1-7 -----	1-14
X	US 5 162 423 A (BASF AG) 10 November 1992 (1992-11-10) the whole document -----	1-14

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 00/07616

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4535124	A	13-08-1985	DE 3339001 A	17-01-1985
			DE 3462048 D	19-02-1987
			EP 0131202 A	16-01-1985
			JP 1923239 C	25-04-1995
			JP 6051833 B	06-07-1994
			JP 60036558 A	25-02-1985
US 5420181	A	30-05-1995	DE 4221935 A	05-01-1994
			CA 2099464 A	04-01-1994
			DE 59305932 D	30-04-1997
			EP 0576950 A	05-01-1994
			ES 2099319 T	16-05-1997
			JP 6073266 A	15-03-1994
US 4880875	A	14-11-1989	DE 3615607 A	12-11-1987
			DE 3765993 D	13-12-1990
			EP 0244856 A	11-11-1987
US 4677162	A	30-06-1987	CA 1239239 A	12-07-1988
US 4868235	A	19-09-1989	DE 3735754 A	03-05-1989
			EP 0312929 A	26-04-1989
US 5162423	A	10-11-1992	DE 3939046 A	29-05-1991
			DE 59009092 D	22-06-1995
			EP 0429957 A	05-06-1991